


TECHNICAL INFORMATION

MARUU SECCHAKU

1 . ITEM

KOUTEIYOU F#75 3 CLEARFILM

2 . CONSTRUCTION



3 . TEST DATA

Properties	Item	Units	Results	Test Methods
Face Material	Thickness	μm	75	JIS-C-2318
	Tensile Strength	N/mm^2	More than 166	JIS-C-2318
Adhesive	Adhesion (PET)	$\text{N}/25\text{mm}$	0.05	MARUU Method
	Holding Power	Sec.	NC 40000	
Release Liner	Thickness	μm	25	JIS-C-2318
	Weight	g/m^2	35	JIS-C-2318
	Tensile Strength	N/mm^2	More than 166	JIS-C-2318