


TECHNICAL INFORMATION

MARUU SECCHAKU

1 . ITEM

CellularPET#50 SP-H White Kraft

2 . CONSTRUCTION



3 . MATERIALS

Face Material : Polyester Mat film

Adhesive : Acrylic type adhesive (Solvent type) (Removable Adhesion)

Release Liner : Kraft paper both side is polyethylene laminated and one side silicone coated.

4 . TEST DETA

Properties	Item	Units	Results	Test Methods
Face Material	Thickness	μm	50	JIS-C-2318
	Tensile Strength	N/mm^2	More than 108	JIS-C-2318
Adhesive	Adhesion (Stainless)	$\text{N}/25\text{mm}$	10.7	MARUU Method
	Holding Power	Sec.	NC 40000	
Release Liner	Thickness	μm	165	JIS-P-8118
	Weight	g/m^2	145	JIS-P-8124
	Tensile Strength	MD CD	$\text{N}/15\text{mm}$	More than 137 More than 88