


TECHNICAL INFORMATION

MARUU SECCHAKU

1 . ITEM

Gold Bright#50 Strong Adhesion PGS

2 . CONSTRUCTION



3 . MATERIALS

Face Material : Polyester Gold Bright film

Adhesive : Acrylic type adhesive (Solvent type)

Release Liner : Blue Glassine one side is polyethylene laminated and silicone coated.

4 . TEST DETA

Properties	Item	Units	Results	Test Methods
Face Material	Thickness	μ m	50	JIS-C-2318
	Tensile Strength	N/mm ²	More than 166	JIS-C-2318
Adhesive	Adhesion (Stainless)	N/25 mm	11.7	MARUU Method
	Holding Power	Sec.	NC 40000	
Release Liner	Thickness	μ m	90	JIS-P-8118
	Weight	g/m ²	94	JIS-P-8124
	Tensile Strength	MD	N/15mm	More than 83
CD		More than 78		