


TECHNICAL INFORMATION

MARUU SECCHAKU

1 . ITEM

OPP#40 Standard Adhesion White Glassine

2 . CONSTRUCTION



3 . MATERIALS

Face Material : Polypropylene Clear film

Adhesive : Acrylic type adhesive (Solvent type)

Release Liner : White Glassine one side is polyethylene laminated and silicone coated.

4 . TEST DATA

Properties	Item	Units	Results	Test Methods
Face Material	Thickness	μm	40	JIS-C-2318
	Tensile Strength	N/mm^2	More than 127	JIS-C-2318
Adhesive	Adhesion (Stainless)	$\text{N}/25\text{mm}$	5.4	MARUU Method
	Holding Power	Sec.	NC 40000	
Release Liner	Thickness	μm	86	JIS-P-8118
	Weight	g/m^2	87	JIS-P-8124
	Tensile Strength	MD	$\text{N}/15\text{mm}$	More than 98
	CD		More than 68	