


## TECHNICAL INFORMATION

MARUU SECCHAKU

### 1 . ITEM

KOUTEIYOU F#75    24   CLEARFILM

### 2 . CONSTRUCTION



### 3 . TEST DATA

Properties	Item	Units	Results	Test Methods
Face Material	Thickness	$\mu\text{m}$	75	JIS-C-2318
	Tensile Strength	$\text{N}/\text{mm}^2$	More than 166	JIS-C-2318
Adhesive	Adhesion ( PET )	$\text{N}/25\text{mm}$	0.24	MARUU Method
	Holding Power	Sec.	NC 40000	
Release Liner	Thickness	$\mu\text{m}$	25	JIS-C-2318
	Weight	$\text{g}/\text{m}^2$	35	JIS-C-2318
	Tensile Strength	$\text{N}/\text{mm}^2$	More than 166	JIS-C-2318