


# TECHNICAL INFORMATION

MARUU SECCHAKU

## 1. ITEM

PET#50 Reitou-Hamyou PGS

## 2. CONSTRUCTION



## 3. MATERIALS

Face Material : Polyester Clear film

Adhesive : Acrylic type adhesive (Solvent type)

Release Liner : Blue Glassine one side is polyethylene laminated and silicone coated.

## 4. TEST DATA

Properties	Item	Units	Results	Test Methods
Face Material	Thickness	$\mu$ m	50	JIS-C-2318
	Tensile Strength	N/mm <sup>2</sup>	More than 166	JIS-C-2318
Adhesive	Adhesion (Stainless)	N/25 mm	12.7	MARUU Method
	Holding Power	Sec.	NC 40000	
Release Liner	Thickness	$\mu$ m	90	JIS-P-8118
	Weight	g/m <sup>2</sup>	94	JIS-P-8124
	Tensile Strength	MD	N/15mm	More than 83
CD		More than 78		